

## SCITUATE CONCRETE PIPE

### Reinforced Concrete Pipe O-ring joint

#### 24" O-Ring Joint Reinforced

#### Design Notes:

1. MFG. in accordance with ASTM Spec. C76 & AASHTO Spec. M170, Wall B.
2. Cement Type II
3. Concrete Strength Class III & IV 4000 P.S.I. Class V 6000 P.S.I.
4. Circum. Reinforcement:  
Class III      0.10 Sq. in. per. ft.  
Class IV      0.27 Sq. in. per. ft.  
Class V      0.30 Sq. in. per. ft.
5. laying length 8' - 0"
6. Rubber Gasket ASTM Spec. C443 and C361

