

## SCITUATE CONCRETE PIPE

### Reinforced Concrete Pipe O-ring joint

#### 42" O-Ring Joint Reinforced

#### Design Notes:

1. MFG. in accordance with ASTM Spec. C76 & AASHTO Spec. M170, Wall B.
2. Cement Type II
3. Concrete Strength Class III & IV 4000 P.S.I. Class V 6000 P.S.I.
4. Circum. Reinforcement:

Class III	0.21 Sq. in. per. ft. Inner Cage
	0.16 Sq. in. per. ft. Outer Cage
Class IV	0.35 Sq. in. per. ft. Inner Cage
	0.26 Sq. in. per. ft. Outer Cage
Class V	0.60 Sq. in. per. ft. Inner Cage
	0.45 Sq. in. per. ft. Outer Cage
5. laying length 8'- 0"
6. Rubber Gasket ASTM Spec. C443 and C361

